

# **VELLUTO FIORENTINO**

# SCHEDA TECNICA

Revisione : 03/05/2023

Prodotto: Velluto Fiorentino Categoria: Eleganza Italiana Azienda: Loggia

#### **General Characteristics**

Covering of great charm with the reflections of silk and the touch of velvet, for fine finishes for both ancient and modern environments with a high decorative effect

## **Application**

Suitable for interior decoration, such as walls and plasters, pre-treated with washable acrylic

#### Media Preparation



Before applying the VELLUTO FIORENTINO effect, it is necessary to proceed with an adequate preparation of the surface by means of powder or paste fillers (such as FLYSTUK), subsequently smoothed with abrasive paper (a grain type P120 is recommended) after about 12 hours from the end of the application. After sanding, proceeding with the eventual elimination of dirt and dust, apply a coat of FISSACRIL acrylic fixative diluted with water in the ratio 1:1 / 1:3. 4-5 hours after applying the fixative, apply 2 coats of Universal Primer using a roller, spaced about 5-6 hours apart. The Universal Primer must have the same tone of color that was chosen for the Florentine velvet.

#### **Application Methods**



Stainless steel spatulas or trowel: Ready to use. If necessary, add water for special needs.

After Universal Primer has dried, apply a first coat of silk stucco using a steel trowel evenly over the entire surface. After 6-8 hours, apply a second coat of silk stucco evenly over a surface of 2-3 m2 and decorate according to the desired effect in fresco, crossing the spatula strokes in various directions until a silk-velvet effect is obtained.

Application temperature:	+5 ÷ +35	°C
Relative humidity of application:	< 85%	
Recommended thickness:	0,5 ÷ 1	µm per coat
Dust dry:	4 ÷ 6	h
Repaintable after:	12	h
Deep dry:	24	h
Tool cleaning:	WATER	

### Painting:



The product can be colored with the tinting systems of the L'ANGELO, L'ANGELO OX and MAXXI lines, as well as with the universal colorants available on the market.

It is advisable to mix different manufacturing batches of the same color together to avoid possible differences in tone during application.

Specific weight:	0,9 ÷ 1,0	Kg/I
Viscosity:		cPs
pH:	7-8	
Solid in weight:	30%	
Theoretical yield:	4 – 5	mq/l
Color:	Card colors	
Appearance:	Silk - Velvet	
Packs:	0,75 - 4 - 14	I

#### Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months.

After use carefully close the package and store it upside down.

Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

#### Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

#### Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

# Loggia Industria Vernici S.r.I. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

BVQI certified company for the UNI EN ISO 9001-2000 quality system.