

# BASIC 69

## SCHEDA TECNICA

Revisione : 16/02/2022

Prodotto: **Basic 69**  
Categoria: Linea Basic  
Azienda: Loggia

## General Characteristics

Super-matt paint for interior with high washability and excellent coverage. Optimal application on all the most common plasters used indoors and on plasterboard. Washable wall paint for interiors with high coverage, high yield, ease of use, masking opaque appearance.

## Application

Suitable for indoor application on lime-based hydraulic binder mortar plasters finished with civil finish, on gypsum-based finishing bases and plasterboard panels

## Preparation



**New Internal Surfaces:** Make sure that the substrate is perfectly dry and cured - not less than 4 weeks for civil plasters and 2 weeks for premixed plasters. If necessary, fill any holes or imperfections with FLYSTUK and sand; finally clean the surfaces. Then apply a coat of FISSACRIL insulator and after 4-6 hours paint with two coats of BASIC 69 following the technical instructions below.



**Internal Painted Surfaces:** Eliminate any traces of mold by brushing off the efflorescence after treating them with acid. Then sanitize with a coat of MUFFACID. Remove flaking residues of old paint and, if necessary, fill and smooth imperfections with FLYSTUK; sand and clean the surfaces. Then apply a coat of FISSACRIL insulator and after 4-6 hours paint with two coats of BASIC 69 following the technical instructions below.



## Application Methods



**Brush:** Dilute 25-30% with water for both the first and second coat. Wait 4 - 5 hours between one application and the next.

**Roller:** Dilute 20-25% with water for both the first and second coat. Wait 4 -5 hours between one application and the next.

Airless: Dilute 50% with water - Nozzle 0.46 - 0.53 mm (0.018 - 0.021 inch) Pressure: 160 - 180 bar.

Application temperature:	+5 +35	°C
Relative humidity of application:	<85%	
Recommended thickness:	35-50	µm per coat
Dust dry:	0.5	h
Repaintable after:	4-5	h
Deep dry:	12	h
Tool cleaning:	water	

## Painting:



The product can be colored with universal dyes on the market. However, it is advisable to use only pastel and light colors.

It is advisable to mix different manufacturing batches of the same color to avoid possible differences in shades during application.

Specific weight:	1.48 1.52	Kg/l
Viscosity:	14000-16000	cPs
pH:	8-9	
Solid in weight:	63.5	
Theoretical yield:	14-16	mq/l
Recommended coats of paint:	-	
Color:	white and color folder	
Packs:	4-14	

### CLASSIFICATION ACCORDING EN 13300

Measure	Norm	Classification	Result
Resistance to wet brushing	ISO 11998	Class 1	< 5 µm 200 cycles
Gloss	ISO 2813	Super matt	< 5 (geometry 85°)

### CLASSIFICATION ACCORDING UNI 10795

Measure	Norm	Classification	Result
Covering power (Ywhite/Yblack)	UNI 11271	Class 1	>= 99,5

## Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months

After use carefully close the package and store it upside down.



Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

## Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

## Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

**Loggia Industria Vernici S.r.l.** Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. [www.loggia.it](http://www.loggia.it), E-mail [commerciale@loggia.it](mailto:commerciale@loggia.it).

**BVQI certified company for the UNI EN ISO 9001-2000 quality system.**