

CASABLANC

SCHEDA TECNICA

Revisione : 03/02/2022

Prodotto: **Casablanc**

Categoria: Idropitture per Interni

Azienda: Loggia

General Characteristics

Thixotropic breathable wall paint based on special vinyl copolymers and selected synergic extenders. Easy applicability and good coverage.

Application

Suitable for painting: ceilings, bathrooms, kitchens, interior walls. Applicable on plasters based on hydraulic binders, gypsum or plasterboard, and mixtures of various nature absorbing, both new and old, provided they are not powdering.

Media Preparation



New Internal Surfaces: Make sure the substrate is perfectly dry and seasoned - no less than 4 weeks for civil plaster and 2 weeks for premixed plasters. If necessary, fill any hole or imperfection with FLYSTUK and sand; finally clean the surfaces. Then apply a coat of FISSAMUR insulation and after 4-6 hours two coats of CASABLANC following the technical instructions below.



Painted Internal Surfaces: Remove any traces of mold by brushing off efflorescence after treating it with acid. Then sanitize with a hand of MUFFACID. Remove flaky residues of old paint and, if necessary, fill and smooth the imperfections with FLYSTUK; sand and clean the surfaces. Then apply a coat of FISSAMUR insulation and after 4-6 hours two coats of CASABLANC following the technical instructions below.



Application Methods



Brush: Dilute to 20-30% with water for both the first and second coat. Wait 4-5 hours between one application and the next.



Roller: Dilute to 20% with water for both the first and second coat. Wait 4-5 hours between one application and the next.

Airless: In airless applications, the dilution varies depending on the equipment and pressure used.



Application temperature:	+5 ÷ +35	°C
Relative humidity of application:	< 85%	
Recommended thickness:	35 ÷ 40	µm per coat
Dust dry:	0,5	h
Repaintable after:	4 ÷ 5	h
Deep dry:	24	h
Tool cleaning:	with water	

Painting:



The product can be colored with the universal dyes that can be found on the market, but it is advisable to make only pastel shades.

It is advisable to mix different batches of the same color together to avoid possible differences in tone during application.

Specific weight:	1,72 ÷ 1,76	Kg/l
Viscosity:	14.000 ÷ 18.000	cPs
pH:	8-9	
Solid in weight:	71%	
Theoretical yield:	6	mq/l
Packaging:	2,5 - 5 - 14	l
Color:	White	
Appearance:	Mat	

Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months

After use carefully close the package and store it upside down.



Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and

suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

BVQI certified company for the UNI EN ISO 9001-2000 quality system.