




**LOGGIA**  
industria vernici

# TECHNICAL DATA SHEET

Issue Date: January 10



## Pliosolv

Pliolite Based Fixative.

### General Characteristics

---

**Composition:** PLIOSOLV is a solvent-based fixative for interior and exterior use, formulated with Pliolite resins. This primer penetrates into the plaster and seals the porous surfaces by bonding unrelated parts of them. It provides both a good vapour permeability and an excellent adhesion for finish coatings. Making surface absorption uniform, PLIOSOLV allows colour uniformity during application of paints.

**Recommended Usage:** It is recommended for interior application on plasters and stucco and for exterior use on suitably prepared masonry walls and concrete.

### Preparation

---

**Surface Preparation:**



*Interior new surfaces:* All surfaces must be dry and cured according to the supplier's recommendations – usually about 30 days. Rough surfaces can be filled with putty FLYSTUK to provide a smooth surface; Ensure the support to be coated is clean with dust and dirt removed. Apply one coat of primer PLIOSOLV followed after 12 hours by two coats of wall paint. For the application please refer to the technical methods given below.



*Interior coated surfaces:* Any mildew should be removed before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the surface to dry before applying a coat of fungicide MUFFACID. It requires the use of proper protective equipment. Existing peeled paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull. Coatings in a poor condition should be removed completely. Fill cracks and holes with putty FLYSTUK; then sand smooth. Remove all sanding dust. Apply one coat of primer PLIOSOLV followed after 12 hours by two coats of wall paint. For the application please refer to the technical methods given below.

*Exterior new surfaces:* All surfaces must be dry and cured according to the supplier's recommendations – usually about 30 days. Rough surfaces can be filled with external putty or a mixture of white cement and fine sand (in the ratio of 1:3) to provide a smooth surface; Ensure the support to be coated is clean with dust and dirt removed. Apply one coat of primer PLIOSOLV followed after

12 hours by two coats of wall paint. For the application please refer to the technical methods given below.

*Exterior coated surfaces:* Any mildew should be removed before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the surface to dry before applying a coat of fungicide MUFFACID. That requires the use of proper protective equipment. Existing peeled paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull. Coatings in a poor condition should be removed completely. Fill cracks and holes with external putty or a mixture of white cement and fine sand (in the ratio of 1:3); then sand smooth. Remove all sanding dust. Apply one coat of primer PLIOSOLV followed after 12 hours by two coats of wall paint. For the application please refer to the technical methods given below.

**Warning: Do not paint in direct sun or on a hot surface. Do not apply to wet surfaces.**

## Product Application

---

### Methods:



*Brush:* Use a nylon/polyester or a natural bristle brush.

*Roller:* Use a nap synthetic or lamb's wool roller cover.

Apply the product as such.

**Warning: The addition of fixative to paints can not be considered as a substitute for the application of the fixative itself. Only in the latter case, the fixative penetrates deep into the plaster and allows to standardize the absorption by sealing not consolidated parts of it. The addition of fixative to paints, in fact, increases its resin content, but will not prevent such defects.**

Temperature of application:	+5 ÷ +35 °C	41 ÷ 95 °F
Relative humidity of application:	< 85%	
Touch dry:	30 minutes	
Recoatable after:	12 hours	
Completely Cured:	7 days	
Cleaning tools:	by synthetic or nitro thinner	

## Technical Properties

---

Density:	0.95 - 1	Kg/L	
Viscosity:			
pH:			
Weight Solids:	12.5%		
Coverage:	12 - 15	m <sup>2</sup> /L	490 - 610 sq ft/gal
Colour:	Clear		
Gloss Levels:	Translucent		
Pack Size:	0.75 - 5 - 20	L	

## Storage

---



Shelf-life: 2 years in original tightly closed containers away from direct sunlight and excessive heat.

The can should be resealed and stored tightly closed to prevent evaporation of the product and entry of air. Store it upside down after use.



Min storage temperature: +5°C (41°F)

Max storage temperature: +30°C (86°F)

## Safety Precautions

---

Refer to the Material Safety Data Sheet before use.

**WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects. For more information about how to remove old lead paint safely contact your local health authority.**

---

## General Information

---

Every care is taken to ensure that the information provided in this technical data sheet is accurate. **Loggia Industria Vernici S.r.l.** takes no responsibility for the results obtained through the use of this product in as much as it is not possible for **Loggia Industria Vernici S.r.l.** to check or control the application method used. For this reason, we recommend that you check carefully that each product chosen, is suitable for each individual use to which it is put.

---

**Loggia Industria Vernici S.r.l.** Via Colle d'Alba di Levante - 04016 B.go S. Donato - Sabaudia (LT) - ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. [www.loggia.it](http://www.loggia.it), E-mail [commerciale@loggia.it](mailto:commerciale@loggia.it).

**Company with Certified Quality System by BVQI according to UNI EN ISO 9001:2000.**