



LOGGIA
industria vernici

TECHNICAL DATA SHEET

Issue Date: January 10



Rustik

Cotto Tiles Treatment.

General Characteristics

Composition: RUSTIK is a solvent-based fixative for interior and exterior use, formulated with methacrylate copolymers. This primer penetrates into the tile and protects and improves the appearance of it.

Recommended Usage: It is recommended for interior and exterior application on cotto tiles.

Preparation

Surface Preparation:



Interior or Exterior surfaces: Ensure the support to be coated is clean with dust and dirt removed. Apply one or two coats of primer RUSTIK. For the application please refer to the technical methods given below.

Product Application

Methods:



Brush or Roller: Dilution depends on the absorbing power. It is possible to dilute it by up to 100% by volume with synthetic thinner.

Temperature of application:	+5 ÷ +35 °C	41 ÷ 95 °F
Relative humidity of application:	< 85%	
Touch dry:	30 minutes	
Recoat after:	12 hours	
Completely Cured:	7 days	
Cleaning tools:	by synthetic or nitro thinner	

Technical Properties

Density:	0.95 - 1 Kg/L	
Viscosity:		
pH:		
Weight Solids:	22.5%	
Coverage:	12 – 15 m ² /L	490 – 610 sq ft/gal
Colour:	Clear	
Gloss Levels:	Translucent	
Pack Size:	0.75 – 5 – 20 L	

Storage



Shelf-life: 2 years in original tightly closed containers away from direct sunlight and excessive heat.

The can should be resealed and stored tightly closed to prevent evaporation of the product and entry of air. Store it upside down after use.



Min storage temperature: +5°C (41°F)

Max storage temperature: +30°C (86°F)

Safety Precautions

Refer to the Material Safety Data Sheet before use.

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects. For more information about how to remove old lead paint safety contact your local health authority.

General Information

Every care is taken to ensure that the information provided in this technical data sheet is accurate. **Loggia Industria Vernici S.r.l.** takes no responsibility for the results obtained through the use of this product in as much as it is not possible for **Loggia Industria Vernici S.r.l.** to check or control the application method used. For this reason, we recommend that you check carefully that each product chosen, is suitable for each individual use to which it is put.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

Company with Certified Quality System by BVQI according to UNI EN ISO 9001:2000.