

FLYSTUK IN POLVERE

SCHEDA TECNICA

Revisione : 21/10/2022

Prodotto: **Flystuk in polvere**
Categoria: Stucchi Rasanti e Colle
Azienda: Loggia

General Characteristics

Powder filler based on specific micronized solid resins, retardants, gypsum mixtures and selected fillers. Excellent adhesion, good workability. Ease of application and preparation. Controlled water retention. High resistance and sandability.

Application

Filling product for wall and wood. Suitable for interiors for the correction of craters and lesions on the supports to be painted.

Preparation



New Internal Surfaces: Make sure that the substrate is perfectly dry and cured - not less than 4 weeks for civil plasters and 2 weeks for premixed plasters. Fill any holes or imperfections with FLYSTUK following the technical instructions below and sand down; finally clean the surfaces.



Internal Painted Surfaces: Eliminate any traces of mold by brushing off the efflorescence after treating them with acid. Then sanitize with a coat of MUFFACID. Remove flaking residues of old paint; apply a preventive coat of FISSAMUR on substrates that are too chalky. Fill and smooth imperfections with FLYSTUK following the technical instructions below; sand and clean the surfaces.



Application Methods



Trowel, Spatula and American Spatula: mix the product well 2: 1 with water until a homogeneous paste is obtained. Workability time 80 minutes. Apply the product by proceeding with subsequent smoothing with a trowel or steel spatulas, to fill cracks and depressions.

Application temperature:	+5 ÷ +35	°C
Relative humidity of application:	< 85%	
Recommended thickness:	0,5 ÷ 1	µm per coat
Dust dry:	1	h
Repaintable after:	6	h
Tool cleaning:	water	
Specific weight:	1,7 ÷ 1,8	Kg/l
pH:	7 ÷ 8	
Solid in weight:	68%	
Theoretical yield:	0,5	m ² /k
Color:	white	
Aspect:	matt	
Packaging:	1 - 5 - 20	k

Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months.



After use carefully close the package and store it upside down.

Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

BVQI certified company for the UNI EN ISO 9001-2000 quality system.