

FLYSTUK ALTO SPESSORE

SCHEDA TECNICA

Revisione : 02/07/2024

Prodotto: **Flystuk alto spessore**
Categoria: Stucchi Rasanti e Colle
Azienda: Loggia

General Characteristics

Paste filler based on specific vinyl emulsions, gypsum mixtures and micronized fillers. Excellent adherence, workability and smoothness. Ease of application. High resistance and excellent sandability.

Application

Excellent filling power and sandability with fast drying and low shrinkage. Indicated for the preparation of surfaces that have to be painted. Excellent for smoothing interior walls.

Media Preparation



The surface must be clean, free from grease or wax. Eliminate non-adherent or detaching parts. In case of powdery substrate, apply a coat of ISOL 45. In case of cracks open them using a specific electric tool and carefully remove all traces of dirt or dust.



New internal surfaces: make sure that the surface is perfectly dry and seasoned - no less than 4 weeks for civil plasters and 2 weeks for premixed plasters. Fill any hole or imperfection with FLYSTUK ALTO SPESSORE following the technical instructions below and sand; finally clean the surfaces.



Internal Painted Surfaces: eliminate any trace of mold by brushing off the efflorescences after having treated them with acid. Then sanitize with a coat of MUFFACID. Remove flaky residues of old paint; pass a preventive coat of FISSAMUR on surfaces that are too chalky. Fill and smooth imperfections with FLYSTUK ALTO SPESSORE following the technical instructions below; sand and clean surfaces

Application Methods



Trowel, spatula and American trowel: apply the product as it is. Proceed by smoothing using a float or steel spatula to fill cracks and depressions.

Application temperature:	+5 ÷ +35	°C
Relative humidity of application:	< 85%	
Recommended thickness:	0,5 - 1	µm per coat
Dust dry:	1	h
Repaintable after:	6	h
Tool cleaning:	with water	

Specific weight:	1,75 ÷ 1,85	Kg/l
pH:	7 - 8	
Solid in weight:	80%	
Theoretical yield:	5-6	mq/Kg x mano
Color	White	
Appearance:	Mat	
Packaging	1- 5-20	kg

Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months.



After use carefully close the package and store it upside down.

Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

BVQI certified company for the UNI EN ISO 9001-2000 quality system.