

MICROPRIMER ATTAC

SCHEDA TECNICA

Revisione : 24/08/2023

Prodotto: **Microprimer attac**

Categoria: Microloggia

Azienda: Loggia

General Characteristics

MICROPRIMER ATTAC is a resinous primer mainly used for low thickness leveling and as an interposition system for particularly smooth surfaces, on difficult surfaces such as bricks, marbles, tiles and ceramics.

Application

MICROPRIMER ATTAC is a particular mixture of polymeric resins and micro-resins in water dispersion loaded with quartz with high stability in an alkaline environment. It comes in the form of a fluid paste with a spreadable consistency. The hardened films obtained with MICROPRIMER ATTAC are slightly flexible and are not soluble in water. These characteristics guarantee the durability of the treatment over time in the most severe conditions and a good level of impermeability.

Surface Preparation



MICROPRIMER ATTAC must be applied on perfectly clean substrates, free from oils, greases, waxes and lime paints. Before applying it, if the substrate is cementitious, proceed with the application of Microuniform. On tiles or marble, after sanding and cleaning, apply the Microprimer Attachment directly..

Application Methods



Brush: Dilute with a maximum of 5% water, making sure that the application is uniform on the surface. After dilution mix the product thoroughly before using it.

Application temperature:	+2 ÷ +35	°C
Relative humidity of application:	< 85%	
Dust dry:	0,5	µm per coat
Repaintable after:	2 ÷ 4	h
Deep dry:	12	h
Tool cleaning:	water	

Specific weight:	1,45	Kg/l
Viscosity:	30.000 ÷ 40.000	cPs
pH:	5,0 – 6,5	
Weight solid:	81%	
Theoretical yeald for thickness of 0,5 mm (brush application):	0,200	Kg/mq
as above spatula :	0,200	Kg/mq
Color:	White, grey	
Appearance:	mat	
Packs:	1 – 5	Kg
Granulometry:	0,3	mm

Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months.



After use carefully close the package and store it upside down.

Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

BVQI certified company for the UNI EN ISO 9001-2000 quality system.

