




**LOGGIA**  
industria vernici

# TECHNICAL DATA SHEET

Revisione: 25 gennaio 2019



## MICROUNIFORM

Impregnant used to uniform and promoting contact.

### General Characteristics

**Product:** it is a resinous primer for the MICROLOGGIA cycle uniforming and as a contact promoter.

**Use:** it is suitable as a base coat anchoring on cementitious substrates, both internal and external and as a uniform before the application of MICROVETRO BI finish Reduces and uniform the absorption of the surface.

### Application

**Preparation of the surface:** verify that the auto levelling floor or the walls are perfectly dried, apply **MICROUNIFORM** and after 2 – 3 h. apply **MICROPRIMER ATTAC**.

Finish cyclo **MICROLOGGIA** wait for 48 – 72 h. after the application of the second coat of **MICROLOGGIA 3** , apply 1 coat of **MICROUNIFORM** and after 2– 4 h. apply **MICROVETRO BI** polished or mat

### Technical application datas

**Method of application:** roller or brush. Ready to use



Temperature of applicazon:	+5 +40	°C
Relative humidity of application:	< 50%	
Typical thickness:	a few millimeter	
Re-coat after:	2-4	h
Tools cleaning:	with water	

### Technical characteristics

density:	1,00	Kg/l
pH:	7 – 8	
Theoretical yeld:	14	m <sup>2</sup> / lt
Packaging:	1 - 5	Kg

## Storage

---



The unopened product, preserved intact in a dry and cool place, has a shelf life of no less than 12 months.

After use, carefully close the package and store it upside down.

Minimum storage temperature: + 5 ° C

Maximum Storage Temperature: + 30 ° C

## Safety Precautions

---

**For all information related to handling of the product and its proper disposal, please refer to the MSDS**

## Warnings

---

The information contained herein is provided to the best of our knowledge. However, such information and suggestions may not have ANY WARRANTY for the applicator, since the conditions of use are outside of our direct control. It is advised to ensure the suitability of the product to the specific case with preliminary tests.

**Loggia Industria Vernici S.r.l.** Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. [www.loggia.it](http://www.loggia.it), E-mail [commerciale@loggia.it](mailto:commerciale@loggia.it).

**BVQI certified company for the UNI EN ISO 9001-2000 quality system.**