

# STUCCO P3D ALTO SPESSORE IN POLVERE

## SCHEDA TECNICA

Revisione : 26/03/2025

Prodotto: **Stucco p3d alto spessore in polvere**

Categoria: Plasma 3D

Azienda: Loggia

### General Characteristics

Powder filler for Bioplasma 3d and Moquette cycle, with excellent adhesion and workability, excellent thixotropy, ease of application, high resistance and excellent sandability.

### Application

Filler primer for internal use, used to mask the joints of tiled floors, porcelain stoneware, etc. to obtain a smooth surface..

### Preparation of the surface



In case of presence of dirt, oil or non-stick stains, act on the surface mechanically, abrading with specific paper or sandpaper or with specific detergents and ensure that they are perfectly neutralised before proceeding to the subsequent phases.



### Application Methods



Stainless steel trowel and 3 mm notched trowel: Apply a first coat of STUCCO P3D FLOOR ALTO SPESSORE IN POWDER with a notched trowel to create thickness, inserting a 75 g/m2 fibre mesh, in order to obtain total coverage of the joints. Apply the second coat after 4-6 hours. After 12 hours, once dry, sand the surface with 100 grit and apply a coat of PRIMER P3D FLOOR with a roller. After 2-4 hours, continue with the desired decorative cycle: apply a coat of primer INTERMEDIAL P3D FLOOR to continue with BIPLASMA 3d, PRIMAMOQUETTE to continue with the application of the MOQUETTE (consult the relevant technical data sheets).



Dilution: 3:1 with water (3 parts of powder product and 1 of water).

|                                   |                 |             |
|-----------------------------------|-----------------|-------------|
| Application temperature:          | +5 +40          | °C          |
| Relative humidity of application: | < 50%           |             |
| Recommended thickness:            | few millimeters | µm per coat |
| Sand after:                       | 6 - 8           | h           |
| Repaintable after:                | 24              | h           |
| Tool cleaning:                    | water           |             |

|                    |                       |       |
|--------------------|-----------------------|-------|
| Specific weight:   | 1,75 ÷ 1,85 (diluted) | Kg/l  |
| Viscosity:         |                       | cPs   |
| pH:                | 7 – 8                 |       |
| Solid in weight:   | 72% once diluted      |       |
| Theoretical yield: | 2                     | mq/kg |
| Color:             | white                 |       |
| Appearance:        | mat                   |       |
| Packaging:         | 1 - 5 -15             | kg    |

## **Storage:**



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months.



After use carefully close the package and store it upside down.

Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

## **Safety Precautions:**

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

## **Warnings**

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

**Loggia Industria Vernici S.r.l.** Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. [www.loggia.it](http://www.loggia.it), E-mail [commerciale@loggia.it](mailto:commerciale@loggia.it).

**BVQI certified company for the UNI EN ISO 9001-2000 quality system.**