

PRIMER P3D WALL

SCHEDA TECNICA

Prodotto: **Primer p3d Wall**Categoria: Plasma 3D

Azienda: Loggia

General Characteristics

Primer product formulated with acrylic emulsions.

Application

Used as a fixative on walls in the PLASMA 3D cycle

Media Preparation



New internal surfaces: Make sure that the surface is perfectly dry and seasoned - no less than 4 weeks for civil plasters and 2 weeks for premixed plasters. If necessary fill any holes or imperfections with FLYSTUK and sand, clean the surfaces and then apply a coat of PRIMER P3D WALL following the technical instructions below.

Revisione:

28/08/2023





Internal Painted Surfaces: Eliminate any traces of mold by brushing off the efflorescences after having treated them with acid. Then sanitize with a coat of MUFFACID. Remove flaky residues of old paint and, if necessary, fill and smooth imperfections with FLYSTUK; sand and clean surfaces. Then apply a coat of PRIMER P3D WALL following the technical instructions below.

Application Methods



Brush and Roller: Ready to use. Apply a coat of PRIMER P3D WALL on the entire surface and wait 4-5 hours.

Follow the instructions given on PLASMA 3D technical sheet to proceed with the colored primers and the decor.

Application temperature:	+5 ÷ +35	°C
Relative humidity of application:	< 85%	
Recommended thickness:	not applicable	μm per coat
Dust dry:	0,5	h
Repaintable after:	4-5	h
Deep dry:	24	h
Tool cleaning:	water	

Specific weight:	1	Kg/I		
Viscosity:		cPs		
pH:	7-8			
Solid in weight:	12%			
Theoretical yield:	5-6	mq/l		
Color:	colorless			
Appearance:	Translucent			
Packing:	1 - 5	1		

Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months.

After use carefully close the package and store it upside down.



Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

Loggia Industria Vernici S.r.I. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.