

# PRIMER P3D FLOOR

## SCHEDA TECNICA

Revisione : 24/10/2022

Prodotto: **Primer p3d Floor**

Categoria: Plasma 3D

Azienda: Loggia

### General Characteristics

Acrylic insulation for floor cycle

### Application

Indicated as isolating coat on STUCCO P3D FLOOR ALTO SPESSORE per il ciclo PLASMA 3D I MARMI - BIPLASMA 3D

### Media Preparation



**FLOORING AND TILES:** For a perfect seal on matt, semi-gloss or glossy tiles, roughen the surface by sanding with specific paper or sander. Subsequently, to eliminate any unevenness due to the joints, a fiber mesh must be inserted when applying STUCCO P3D FLOOR and sanded. Then pass PRIMER P3D FLOOR. Wait 4-6 hours and apply one or two coats of INTERMEDIAL P3D FLOOR. Check the technical data sheets of the PLASMA 3D I MARMI - BIPLASMA 3D products for the application indications of the finishing product.

### Application Methods



Brush and Roller: ready to use

Airless: In airless applications the dilution varies depending on the equipment and pressure used.

Application temperature:	+5 ÷ +35	°C
Relative humidity of application:	< 85%	
Recommended thickness:	non applicable	µm per coat
Dust dry:	0,5	h
Repaintable after:	4 - 5	h
Deep dry:	24	h
Tool cleaning:	water	

Specific weight:	1	Kg/l
Viscosity:		cPs
pH:	7-8	
Solid in weight:	25%	
Theoretical yield:	9 – 10	mq/l
Color	without color	
Aspect:	Translucide	
Packs:	1 - 5 – 10 – 20	l

## Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months.



After use carefully close the package and store it upside down.

Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

## Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

## Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

**Loggia Industria Vernici S.r.l.** Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. [www.loggia.it](http://www.loggia.it), E-mail [commerciale@loggia.it](mailto:commerciale@loggia.it).

**BVQI certified company for the UNI EN ISO 9001-2000 quality system.**