

MICROVETRO MONO LUCIDO

SCHEDA TECNICA

Revisione : 03/09/2025

Prodotto: **Microvetro Mono Lucido**

Categoria: Plasma 3D

Azienda: Loggia

General Characteristics

Transparent, water-based urethane resin-based glaze; odorless, non-yellowing, and weather-resistant. It forms an elastic, abrasion-resistant, and easy-to-clean film.

Application

MICROVETRO Mono is indicated as a "glazing effect" protector for wall surfaces to which both organic and mineral decorative effects have been applied, giving the surface the appearance of a vitrified surface. It is also suitable for wooden surfaces and artefacts.

Preparation

Make sure the surface to be treated is completely dry and free of dirt before applying.



Apply MICROVETRO Mono when the decorative surface is completely dry (at least 3 days after application) to minimize the formation of air bubbles and chipping.

Application Methods



Apply a first coat of MICROVETRO Mono using a roller, using enough material to form a full coat. After each coat, roll the surface lightly, without pressure, to promote a bubble-breaking effect. Avoid reapplying the clear coat, minimizing overlaps to reduce the formation of streaks during drying.



After 6-8 hours, apply the second coat.

Application temperature:	+10 ÷ +30	°C
Relative humidity of application:	< 50%	
Dust dry	1 ÷ 2	h
Deep dry:	7	h
Repaintable after:	8	h
Tool cleaning:	soap and water, then thinner	

Specific weight:	1,05	Kg/l
Solid in weight:	42%	
Theoretical yield:	14-16	mq/l
color	Transparent	
appearance	Polished	
packs	1 - 2,5	l

Storage:



The unopened product, stored intact in a dry and cool place, has 12 months storage life .

Minimum storage temperature: + 5 ° C



Maximum storage temperature: + 30 ° C

Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

BVQI certified company for the UNI EN ISO 9001-2000 quality system.