

MICROVETRO MONO OPACO

SCHEDA TECNICA

Prodotto: Microvetro Mono Opaco

Categoria: Plasma 3D

Azienda: Loggia

General Characteristics

Transparent vitrifying varnish, based on water-based urethane resins; odorless, non-yellowing, resistant to atmospheric agents. It forms an elastic film, resistant to rubbing and easy to clean.

Application

MICROVETRO Mono is indicated as a "glazing effect" protector for wall surfaces to which both organic and mineral decorative effects have been applied, giving the surface the appearance of a vitrified surface. It is also suitable for wooden surfaces and artefacts.

Preparation



Wood/metal substrate preparation: Make sure the surface to be treated is completely dry and free of dirt before applying MICROVETRO. Apply MICROVETRO following the instructions below.

Revisione:

26/09/2025

Mineral and/or decorative substrate preparation: Before applying MICROVETRO Mono, make sure the surface is completely dry to minimize the formation of air bubbles and chipping. Follow the application instructions below.

Application Methods



Apply MICROVETRO Mono evenly with the roller in sufficient quantity to make the hand full; pass a final roll over the surface lightly, without pressure, to favor the bubble-breaking effect; avoid going back over the already applied transparent, minimizing overlaps in order to reduce the formation of halos during drying. After 6-8 hours proceed with the application of the second coat.

The paint film appears milky white, but when drying it becomes perfectly transparent and shiny.

Application temperature:	+20 ÷ +35	°C
Relative humidity of application:	<= 50%	
Recommended thickness:	0,5 ÷ 1,5	μm per coat
Dust dry:	2 - 4	h
Deep dry:	12 - 24	h
Tool cleaning:	water	

Specific weight:	1.01	Kg/I	
Viscosity:	5000	cPs	
pH:	7 - 8		
Solid in weight:	82%		
Theoretical yield:	on smooth surfaces 14-16	mq/l	
	(on other surfaces it varies depending on the substrate)		

Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months.



Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

Specifications

Glossy moldable decorative coating. Preparation of the substrate as recommended for walls or floors. Application of a coat of MICROVETRO in the quantity required to obtain a suitable film thickness when dry. All must be carried out in compliance with the application standards, with a cost of € per square meter including material and installation

Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

Loggia Industria Vernici S.r.I. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.