

STUCCO VELATO METALLICO BRONZO

SCHEDA TECNICA

Revisione : 21/09/2023

Prodotto: **Stucco velato metallico Bronzo**

Categoria: Plasma 3D

Azienda: Loggia

General Characteristics

Translucent spatula coating for interiors, formulated with metallic micas and very resistant acrylic resins.

Application

For metallic finish on 3D PLASMA or possibly on washable smooth paints.

Preparation



Proceed with the elimination of any dirt and dust present on the surface to be treated



Application Methods



Stainless steel spatulas: Ready to use. Apply the product with the stainless steel spatula, working it irregularly on the surface. It is possible to apply a second coat 3 – 4 hours after the first.

Spray: Dilute 30-35% with water for both the first and second coat. Wait 6-8 hours between one application and the next. Gun pressure 3-4 Atm, nozzle diameter 1.7-2 mm.

Airless: In airless applications the dilution varies depending on the equipment and pressure used. Indicative values: 5% dilution with water and nozzles of 0.017-0.019", at a pressure of 120-150 Atm.

Application temperature:	+5 ÷ +35	°C
Relative humidity of application:	< 85%	
Recommended thickness:	30	µm per coat
Dust dry:	2	h
Repaintable after:	3-4	h
Deep dry:	24	h
Tool cleaning:	water	

Specific weight:	0,9 ÷ 1	Kg/l
Viscosity:		cPs
pH:	7-8	
Solid in weight:	40%	
Theoretical yield:	11 – 12	mq/l
Recommended coats of paint:	Silver Gold Bronze Copper	
Color:	Metallic	
Appearance:	0,75 - 4	

Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months.



After use carefully close the package and store it upside down.

Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) –
ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

BVQI certified company for the UNI EN ISO 9001-2000 quality system.