

VANESIA

SCHEDA TECNICA

Revisione : 02/05/2023

Prodotto: **Vanesia**
Categoria: Eleganza Italiana
Azienda: Loggia

General Characteristics

Vanesia is an interior covering of great charm with the reflections of silk.

Application

Due to its elegance, Vanesia is ideal for the protection and decoration of the internal walls of prestigious ancient or modern buildings, such as villas, hotels, banks and offices.

Media Preparation



Thoroughly clean the surfaces (walls or plasterboard) to be decorated carefully removing all impurities using abrasive paper. Prepare the surface with powder or paste fillers (such as Flystuk). 12 hours after the end of the smoothing filler application, sand with P120-P150 type abrasive paper. Apply a coat of FISSACRIL vinyl fixative diluted 1:4 with water. Wait 4-5 hours and apply 1-2 coats of colored Acrylic Primer of the same shade as the color of the chosen Vanesia.

Application Methods



Plafononcino or flat brush: ready to use. For special needs add 5 – 10% of water.

Wait 6-8 hours from the end of the application of the Primer and proceed with the drafting of a first coat of Vanesia crossing the brushstrokes in an irregular way until the completion of the wall. After 4-6 hours, apply a second coat following the same instructions already taken for the first one until the desired effect is obtained.

Application temperature:	+5 ÷ +35	°C
Relative humidity of application:	< 85%	
Recommended thickness:	35 ÷ 50	µm per coat
Dust dry:	1 ÷ 2	h
Repaintable after:	6-8	h
Deep dry:	24	h
Tool cleaning:	water	

Painting:



The product can be colored with the tintometric systems of the L'ANGELO and L'ANGELO OX lines, as well as with the universal colorants available on the market.

It is advisable to mix different manufacturing batches of the same color together to avoid possible differences in tone during application.

Specific weight:	0,9 ÷ 1,0	Kg/l
Viscosity:		cPs
pH:	7-8	
Solid in weight:	30%	
Theoretical yield:	9 – 10	mq/l
Color:	Card colors	
Appearance:	Iridescent silk	
Packs:	0,75 - 4 – 14	

Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months.



After use carefully close the package and store it upside down.

Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) –
ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

BVQI certified company for the UNI EN ISO 9001-2000 quality system.