

MONTENAPOLEONE

SCHEDA TECNICA

Revisione : 03/05/2023

Prodotto: **Montenapoleone**
Categoria: Eleganza Italiana
Azienda: Loggia

General Characteristics

Coating of great charm with satin pearlescence. For fine finishes for both ancient and modern environments.

Application

Suitable for interior decoration, such as walls and plasters, pre-treated with our primer Fond plus. Suitable for the internal finishing of artistically interesting ancient or modern buildings, precisely because of its elegance and refinement.

Media Preparation



Prepare the surface with powder or paste fillers (such as Flystuk). Approximately 12 hours after the end of the application, treat with abrasive paper: a P120 type grit is recommended. Apply a coat of acrylic fixative (such as Fissacrill) diluted with water in the ratio 1:1/1:3 depending on the substrate. After 4-5 hours, apply a coat of FOND PLUS base coat using a roller, approximately 5-6 hours apart.



Applying the finish. After the primer has dried, apply the first coat of Montenapoleone evenly over the entire surface with a steel trowel. After 6-8 hours, apply a second coat of Montenapoleone evenly. When fresh, cross the strokes with the stainless steel spatula proceeding from top to bottom and from right to left



Application Methods



Stainless steel spatulas: Ready to use. If necessary, add water for special needs

Application temperature:	+5 ÷ +35	°C
Relative humidity of application:	< 85%	
Recommended thickness:	0,5 ÷ 1	µm per coat
Dust dry:	2	h
Repaintable after:	4 – 6	h
Deep dry:	24	h
Tool cleaning:	WATER	

Painting:



The product can be colored with the tintometric systems of the L'ANGELO and L'ANGELO OX lines, as well as with the universal colorants available on the market.

It is advisable to mix different manufacturing batches of the same color together to avoid possible differences in tone during application.

Specific weight:	1,2 ÷ 1,3	Kg/l
Viscosity:	8000	cPs
pH:	7-8	
Solid in weight:	72%	
Theoretical yield:	6-9	mq/l
Color:	Color cards	
Appearance:	gold, silver	
Packs:	0,75- 5 -14	l

Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months.



After use carefully close the package and store it upside down.

Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) –
ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

BVQI certified company for the UNI EN ISO 9001-2000 quality system.