

MARMORINO ANTICO

SCHEDA TECNICA

Revisione : 04/10/2023

Prodotto: **Marmorino antico**

Categoria: Linea Impero

Azienda: Loggia

General Characteristics

Coating based on hydrated lime (aged 12 months), marble powder, formulated with inorganic pigments, special additives and inert mineral fillers. Excellent resistance to aggressive agents present in industrial and marine areas; furthermore the product is resistant to U.V. and molds

Application

Suitable for use on artistically interesting ancient or modern buildings. The product can be used for internal and external coatings.

Media Preparation



Before applying Marmorino, it is necessary to adequately prepare the surface using powder or paste fillers (such as FLYSTUK), then smoothed with abrasive paper (a grit type P120 is recommended) approximately 12 hours after the end of application. After sanding, proceeding with the eventual elimination of dirt and dust, apply a coat of FISSAMUR vinyl fixative diluted with water in the ratio 1:1 / 1:4. 4-5 hours after applying the fixative, apply 1-2 coats of Vinyl Primer using a roller, spaced about 5-6 hours apart. The Primer must be white or the same tone of color that was chosen for the grout, but with a lower degree of intensity.

Application Methods



Stainless steel spatulas or trowel: Ready to use.

If necessary, add water for special needs. For a better result, apply 3 coats of Marmorino Antico spaced 4-6 hours apart. The first two coats should be well shaved smooth but not shiny. The third coat as a finish must be applied by overlapping the spatula strokes until the wall is completed. Once the wall is finished, polish it using a stainless steel scraper in various directions until the desired brilliance is obtained.

To obtain a more water-repellent effect, after 5-6 days it is possible to shave very lightly using beeswax.

Application temperature:	+5 ÷ +35	°C
Relative humidity of application:	< 85%	
Recommended thickness:	0,5 ÷ 1	mm per coat
Dust dry:	2	h
Repaintable after:	8	h
Deep dry:	24	h
	WATER	

Painting:



The product can be colored with the tinting systems of the L'ANGELO OX line, as well as with the universal oxide-based colorants that are available on the market.

It is advisable to mix different manufacturing batches of the same color together to avoid possible differences in tone during application

Specific weight:	1,35 ÷ 1,40	Kg/l
Viscosity:		cPs
pH:	12 - 14	
Solid in weight:	58%	
Theoretical yield:	2 – 3	mq/kg
Color:	Color cards	
Appearance:	Glossy marble	
Packs:	1 - 5 – 25	Kg

Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months.



After use carefully close the package and store it upside down.

Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the

Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) –
ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

BVQI certified company for the UNI EN ISO 9001-2000 quality system.