




LOGGIA
industria vernici

TECHNICAL DATA SHEET

Revision: June the 27 luglio 2016



Mascara

Changing coating

General Characteristics

Composition: Coating of great charm with pearlescent reflexes, for fine finishes for both ancient and modern environments with a high decorative effect.

Recommended usage: Suitable for indoor use as finish coat of the decorative Marmo Romano.

Preparation

Surface preparation:




Before the application of Mascara it is necessary to prepare the surface with powder or paste putty (such as FLYSTUK). After 12 hours proceed to light sanding with abrasive paper (we recommend a grain such as P120). Clean carefully the surface by removing any kind of dust or dirtiness then dab one coat of acrylic fixative FISSACRIL diluted with water 1:1 / 1:3. After 4-5 hours apply 2 coats of Marmo Romano by using a roll spaced by about 5-6 hours from each other. The Primer can be white or colored.



Product Application


Methods:

Stainless steel spatula or trowel: ready to use. If necessary it can be added some water.



When Marmo Romano is dried (consult the technical data sheet for its application) dab on the entire surface one coat of Mascara with a steel trowel by creating metallic shades. After 4-6 hours apply another coat of Mascara, according to the effect desired.

It can be applied by combining two colors wet on wet and shading off them. The product is available in Silver and Bronze. Silver Mascara can be colored.



Temperature of application:	+5 ÷ +35	°C
Application relative humidity:	< 85%	
Dry film thickness:	0,1 ÷ 1	mm one coat
Touch dry:	4 ÷ 6	h
Repaintable after:	12	h
Completely dried:	24	h
Cleaning tools:	with water	

Colouring



The product can be colored with the Tinting Systems L'ANGELO e L'ANGELO OX as well as with the universal colorants that can be found in commerce. Be careful if different batches of the same color are used; it is recommended to mix them together in order to ensure uniformity to the color during the application.

Technical Properties


Density:	0,9 ÷ 1,0	Kg/l
Viscosity:		cPs
pH:	7-8	
Weight solids:	30%	
Coverage:	7-8	mq/l
Color:	Colori di Cartella	
Aspect:	perlescente metallizzato	
Pack size:	0,75 - 4 - 14	l

Storage



Shelf-life: 2 years in original tightly closed container away from direct sunlight and excessive heat.

The can must be resealed and stored tightly closed upside down after using.



Min storage temperature: +5°C (41° F)

Max storage temperature: +30°C (86° F)

Safety Precautions

Please, refer to the Material Safety Data Sheet before use.

Item Specifications

Changing coating. Preparation of the surface with Flystuck, then one coat of FISSACRIL and two coats of Marmo Romano. Apply then Marmo Romano (see Technical Data) and, once dried, apply MASCARA according to the information provided above with a cost of € per m2, material and pose in work included.

General Information

Every care is taken to ensure that the information provided in this technical data sheet is accurate. Nevertheless Loggia Industria Vernici Srl takes no responsibility for the results obtained by the use of this product since it is not possible for Loggia Industria Vernici Srl to check or control the application method used. For this reason we recommend to check carefully that each product chosen is suitable for the individual use to which it is put.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

Company with Certified Quality System by BVQI according to UNI EN ISO 9001-2000.