

KYMERA TRASPARENTE

SCHEDA TECNICA

Revisione : 20/02/2023

Prodotto: **Kymera trasparente**

Categoria: Linea Impero

Azienda: Example

General Characteristics

Transparent glaze for the protection of Kymera.

Application

24 hours after applying the Kymera Activator, wash the surface with a damp cloth, let it dry and pass a coat of Fissacril dil. 1/3 with water. After 3/4 hours, apply Kymera Trasp finish with a brush or roller.

Application Methods



Brush or Plafononcino: Ready to use. Proceed with the drafting of KYMERA TRASP by crossing the brushstrokes one over the other until the surface is completed.



Application temperature:	+5 ÷ +35	°C
Relative humidity of application:	< 85%	
Recommended thickness:	20 ÷ 35	µm per coat
Dust dry:	4 ÷ 6	h
Repaintable after:	12	h
Deep dry:	24	h
Tool cleaning:	water	

Specific weight:	0,9 ÷ 1,0	Kg/l
pH:	7-8	
Solid in weight:	7,5%	
Theoretical yield:	7 – 8	mq/l
Color:	Transparent	
Appearance:	Mat translucent	
Packaging:	0,500 -1 - 2,5 - 4	l

Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months.



After use carefully close the package and store it upside down.

Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

BVQI certified company for the UNI EN ISO 9001-2000 quality system.