

# SOFFIO

## SCHEDA TECNICA

Revisione : 03/02/2022

Prodotto: **Soffio**

Categoria: Idropitture per Interni

Azienda: Loggia

## General Characteristics

Breathable thixotropic wall paint based on special vinyl-versatic copolymers and selected high-resistance synergistic extenders. Easy to apply and good coverage.

## Application

Suitable for painting ceilings, bathrooms, kitchens and interior walls. Applicable on plasters based on hydraulic binders, gypsum or plasterboard and absorbent conglomerates of various kinds, both new and old, as long as they are not chalking.

## Media Preparation



New Internal Surfaces: make sure that the substrate is perfectly dry and cured - not less than 4 weeks for civil plasters and 2 weeks for premixed plasters. If necessary, fill any holes or imperfections with FLYSTUK and sand; finally clean the surfaces.



Then apply a coat of FISSAMUR insulator and after 4-6 hours paint with two coats of SOFFIO following the technical instructions below.



Painted Interior Surfaces: remove any traces of mold with Risanare Cid.

Then sanitize with a coat of MUFFACID. Remove flaking residues of old paint and, if necessary, fill and smooth imperfections with FLYSTUK; sand and clean the surfaces. Then apply a coat of FISSAMUR insulator and after 4-6 hours paint with two coats of SOFFIO following the technical instructions below.

## Application Methods



Brush: Dilute 20-30% with water for both the first and second coat. Wait 4-5 hours between one application and the next.

Roller: Dilute 20% with water for both the first and second coat. Wait 4-5 hours between one application and the next.



Airless: In airless applications the dilution varies depending on the equipment and pressure used.



Application temperature:	+5 ÷ +35 °C	°C
Relative humidity of application:	< 85%	
Recommended thickness:	35 ÷ 40 µm per coat	
Dust dry:	0,5	h
Repaintable after:	4 ÷ 5	h
Deep dry:	24	h
Tool cleaning:	by water	

## Painting:



The product can be colored with universal dyes available on the market, but only pastel shades are recommended. It is advisable to mix different manufacturing batches of the same color with each other to avoid possible differences in shades during application..

Specific weight:	1.72 ÷ 1.78 Kg/L	Kg/l
Viscosity:	14000 ÷ 18000	cPs
pH:	8-9	
Solid in weight:	71%	
Theoretical yield:	6	mq/l
Pack Size:	2.5 - 5 – 14 L	
Color:	White	
Appearance:	Matt	

## Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months

After use carefully close the package and store it upside down.



Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

## Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

## **Warnings**

---

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

**Loggia Industria Vernici S.r.l.** Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. [www.loggia.it](http://www.loggia.it), E-mail [commerciale@loggia.it](mailto:commerciale@loggia.it).

**BVQI certified company for the UNI EN ISO 9001-2000 quality system.**