

## TECHNICAL DATA SHEET

Revisione: 11 novembre 2014



# Luminor

Changing spotted Finish.

#### General Characteristics

**Composition:** Luminor is a high-quality, polychromatic decorative finish for interior. The glazes

and slightly irregular relief mixed the fantasy of its colors give to the

environment at the same time an antique and precious look.

Recommended usage: Suitable for decorating walls, columns and elements of interior of ancient and

modern buildings both rural or prestigious.

#### Application

#### Surface preparation:





Clean carefully the surfaces (walls or plasterboard) that must be decorated by removing all the impurities by means of abrasive papers. Prepare the surface with putty powder or paste (type Flystuk). After 12 hours of the end of the application of putty sand with abrasive paper type P120-P150. Apply a coat of vinyl FISSAMUR diluted 1: 3 with water. Wait 4-5 hours and apply, by means of a roller, 1-2 coats of PRIMA FOND or UNIVERSAL PRIMER white



#### Application techniques

#### **Application methods:**



Trowel or plastic spatula: Ready to use.

Wait 6-8 hours after the application of the primer and proceed to the application of Luminor by crossing brush movements on an irregular basis until the completion of the wall. Every 4-5 m2 with a little pressure, by means of the plastic spatula or trowel, crush the colored flake with irregular movements, until you get the desired effect. From 4 to 6 hours, the flake will fill in gold or silver film, with a mat effect and reproducing exactly the color of the selected folder.

Temperature of application:	+5 ÷ +35	°C
Humidity for application:	< 85%	
Recommended thickness:	1 ÷ 2	mm
Touch dry:	1 ÷ 2	h
Recoatable after:	4 - 6	h
Completely cured after:	24	h
Tools cleaning:	con acqua	

#### Colouring



The product could be colored with Tinting System L'ANGEL and L'ANGELO OX, as well Universal toners that can be found on the market.

It is recommended to mix different batches to avoid possible differences of shades during the application.

#### Technical properties

Density:	1,05 ÷ 1,15	Kg/l	
Viscosity:		cPs	
pH:	7-8		
Weight solids:	50%		
Coverage:	5 – 6	mq/l	
Colour:	Color Folder		
Aspect:	Spotted, thick, metallic		
Pack size:	0,75 - 4 - 14	1	

## Storage





Shelf-life: not less than 2 years original tightly closed. Store away from direct sun and excessive heat.

The can should be resealed and stored tightly closed. Store it upside down after use.





Min storage temperature: +5°C

Max storage temperature: +5°C

# Safety Precautions

For all information regarding product use and correct product disposal please refer to Safety Data Sheet.

#### Specifications items

**Changing spotted Finish**. Prepare the surface with 1 coat of FISSAMUR and 2 of PRIMA FOND Or UNIVERSAL PRIMER. Apply a slight coat of LUMINOR according to the quantity absorbed by the surface in order to obtain a suitable dry film thickness. All must be made in accordance with the implementing rules, with a cost of €...... for m2 including material and pose in work

### Warnings

All information contained in this data sheet are based on our technical knowledge. However these indication could not have a value of guarantee for applicator considering that conditions of applying of product are out of our control. It is advisable make sure of suitability of the product making previous test.

Loggia Industria Vernici S.r.I. Via Colle d'Alba di Levante - 04016 B.go S. Donato - Sabaudia (LT) - ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

Company with Certified Quality System by BVQI according to UNI EN ISO 9001:2000.