




LOGGIA
industria vernici

TECHNICAL DATA SHEET

Issue Date: January 14



Hellenica

Mouldable High Build Décor Effect.

General Characteristics

Composition: HELLENICA is a mouldable high build coating for interior and exterior use. It has been formulated with elastomeric emulsions and high resistant fillers and pigments. Its lightness allows the tools to move smoothly without much effort, retaining the pattern left by the tool that created it. It provides sufficient open time to allow the creation of effects such as weaving, canvas, travertine etc.

Recommended Usage: It is recommended for application on interior and exterior plasters, suitably prepared masonry walls and concrete.

Preparation

Surface Preparation:



Interior or exterior new surfaces: All surfaces must be dry and cured according to the supplier's recommendations – usually about 30 days. Rough surfaces can be filled with putty FLYSTUK to provide a smooth surface; light sanding with P120 grade abrasive paper will be required. Ensure the support to be coated is clean with dust and dirt removed. One coat of fixative FISSAMUR should be applied (dilute 1:1 - 1:3 with water). For the application of HELLENICA please refer to the technical methods given below.



Interior or exterior coated surfaces: Any mildew should be removed before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the surface to dry before applying a coat of fungicide MUFFACID. It requires the use of proper protective equipment. Existing peeled paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull. Coatings in a poor condition should be removed completely. Fill cracks and holes with putty FLYSTUK; then sand smooth with P120 grade abrasive paper. Remove all sanding dust. One coat of fixative FISSAMUR should be applied (dilute 1:1 - 1:3 with water). For the application of HELLENICA please refer to the technical methods given below.

Product Application

Methods:



Stainless steel Trowel and the appropriate decorative tool: Apply the product as such with a steel trowel and evenly distribute it over the surface in all directions till the final desired effect is got. During withering work the surface with the appropriate decorative tool.

In order to better protect HELLENICA from bad weather conditions and to increase its beauty you can apply on it a coat of decorative coating EFFETTO TAMPONATO SILOSSANICO after 24 hours. Please refer to technical data sheet for methods and application.

Temperature of application:	+5 ÷ +35 °C	41 ÷ 95 °F
Relative humidity of application:	< 85%	
Dry film thickness:	1 ÷ 3 mm	
Touch dry:	4 - 6 hours	
Recoat after:	24 hours	
Completely Cured:	21 days	
Cleaning tools:	by water	

Colouring



This product can be coloured with Tinting Systems L'ANGELO and L'ANGELO OX. In addition it can be tinted with Universal Stainers to obtain customized shades.

Care should be taken when one uses different batches of the same colour. Mix them together to ensure colour uniformity during application.

Technical Properties

Density:	1.15 ÷ 1.25	Kg/L
Viscosity:		
pH:	7 - 8	
Weight Solids:	62%	
Coverage:	1 - 1.5	m ² /Kg
Colour:	Many Colours	
Gloss Levels:	Opaque	
Pack Size:	1 - 5 - 25	Kg

Storage



Shelf-life: 2 years in original tightly closed containers away from direct sunlight and excessive heat.

The can should be resealed and stored tightly closed to prevent evaporation of the product and entry of air. Store it upside down after use.



Min storage temperature: +5°C (41°F)

Max storage temperature: +30°C (86°F)

Safety Precautions

Refer to the Material Safety Data Sheet before use.

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects. For more information about how to remove old lead paint safety contact your local health authority.

General Information

Every care is taken to ensure that the information provided in this technical data sheet is accurate. **Loggia Industria Vernici S.r.l.** takes no responsibility for the results obtained through the use of this product in as much as it is not possible for **Loggia Industria Vernici S.r.l.** to check or control the application method used. For this reason, we recommend that you check carefully that each product chosen, is suitable for each individual use to which it is put.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

Company with Certified Quality System by BVQI according to UNI EN ISO 9001:2000.