

OCEANIA

SCHEDA TECNICA

Revisione : 27/04/2023

Prodotto: **Oceania**
Categoria: Linea Impero
Azienda: Loggia

General Characteristics

Oceania is a highly fascinating acrylic finish for interior decoration with a sandblasted effect that creates an irregular texture that recalls the movement of sea waves; suitable for both classic and modern environments.

Application

Oceania is ideal for the protection and decoration of the internal walls of prestigious ancient or modern buildings, such as villas, hotels, banks and offices.

Media Preparation



Before applying Oceania it is necessary to proceed with an adequate preparation of the surface using smoothing powders or pastes (such as FLYSTUK); 12 hours after applying the skim coat, smooth the support with abrasive paper (a P150 type grit is recommended). After sanding, proceed with the eventual elimination of dirt and dust, apply a coat of FISSACRIL acrylic fixative diluted with water in the ratio 1:1 / 1:3. 4-5 hours after applying the fixative, apply 2 coats of Primer using a roller

Application Methods



Spalter single or double : Dilution of the product: 5-10% with water.

6-8 hours after applying the primer, proceed with the application of Oceania crossing the brushstrokes every 2-3 m² work Oceania with a 10 cm dry spalter creating circles until obtaining the sea wave effect. It is possible to cross two different pearlescent toners and have two nuances, using the double spalter.

Application temperature:	+5 ÷ +35	°C
Relative humidity of application:	< 85%	
Recommended thickness:	50 ÷ 100	µm per coat
Dust dry:	1-2	h
Repaintable after:	6-8	h
Deep dry:	48	h
Tool cleaning:	WATER	

Painting:



It is advisable to mix different manufacturing batches of the same color together to avoid possible differences in tone during application.

Specific weight:	1,45 ÷ 1,55	Kg/l
Viscosity:	5000-10000	cPs
pH:	6-7	
Solid in weight:	60%	
Theoretical yield:	6-7	mq/l
Recommended coats of paint:	Color CARDS	
Color:	GOLDEN SAND, SILVER, DIAMOND	
PACKS:	0,75 - 4	L

Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months.



After use carefully close the package and store it upside down.

Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) –
ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

BVQI certified company for the UNI EN ISO 9001-2000 quality system.