




LOGGIA
industria vernici

TECHNICAL DATA SHEET

Revisione: 10 gennaio 2014



Oro Puro

Changing finishing with glossy and matt golden effect.

General Characteristics

Composition: Precious decorative coating with delicate golden effects, matt and gloss what give special light and elegance to the environments. It is indicated for decorating hotels, villas and luxury shops.

Recommended Usage: It is recommended for indoor decoration of precious modern and antiques buildings.

Preparation

Surface preparation:



Before to apply the product it is necessary to prepare the surface with pasty putty as FLYSTUCK what should be send 12 hours later with sanding paper (grain P150). After sanding is necessary to clean well the surface from dust and dirtiness. Apply 1 coat of acrylic fixative FISSACRIL diluted with water 1:1/1:3. 4/5 hours after apply 1-2 coats or UNIVERSAL PRIMER in the same shade of ORO PURO.



Application techniques

Application methods: *Brush or Roller (trimmed pile roller)* : Product is ready for use.



Application by roller: 6–8 hours after application of Primer proceed with ORO PURO application rolling uniformly over all surface. Apply second coat after 4-6 hours.

Temperature for application:	+5 ÷ +35	°C
Humidity for application:	< 85%	
Recommended thickness:	80 ÷ 120	µm
Touch dry:	2 ÷ 4	h
Recoatable after:	2 - 4	h
Completely cured:	24	h
Tools cleaning:	with water	
Washable after:	30	days

Colouring



The product could be colored with Tinting System L'ANGELO 40X, as well Universal toners.

It is recommended to mix different batches to avoid possible differences of shades during the application.

Technical Properties

Density:	1,1 ÷ 1,2	Kg/l
Viscosity:	6.000 -9.000	cPs
pH:	7-8	
Weight solids:	40%	
Coverage:	8-9	mq/l
Color:	Color Chart	
Gloss level:	gold gloss or matt	
Pack size:	0,75 - 4	l

Storage



Shelf-life: not less than 2 years original tightly closed. Store away from direct sun and excessive heat.

The can should be resealed and stored tightly closed. Store it upside down after use.



Min storage temperature: +5°C

Max storage temperature: +30°C

Safety Precautions

For all information regarding product use and correct product disposal please refer to Safety Data Sheet.

Warnings

All information contained in this data sheet are based on our technical knowledge. However these indication could not have a value of guarantee for applicator considering that conditions of applying of product are out of our control. It is advisable make sure of suitability of the product making previous test.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

Azienda certificata BVQI per il sistema di qualità UNI EN ISO 9001-2000.

