




LOGGIA
industria vernici

TECHNICAL DATA SHEET

Revisione: 10 novembre 2014



Prima Fond

White pasty Primer.

General Characteristics

Composition: Pasty primer made of specific synthetic resins and micronized charges. Excellent adhesion, easy to work and to apply. Good thixotropy that prevents leaking. High resistance.

Recommended Usage: Basic Primer for the decorative : Marmorino Cerato, Marmorino Antico, Platinum Oro and Argento

Application

Surface preparation:



Clean carefully all surfaces (walls or plasterboard) that need to be decorated carefully removing all the impurities by means of abrasive papers. Prepare the surface with putty powder or paste (type Flystuk). After 12 hours of the end of the application of putty sand with abrasive paper type P120-P150. Apply a coat of vinyl FISSAMUR diluted 1: 3 with water. Wait 4-5 hours and apply 1-2 coats of primer, white or the same color of the finish.

Application techniques

Application methods:



Plastering trowel, spatula and American spatula : Apply the product as is. Proceed with subsequent smoothing with a trowel or steel spatula, to obtain a smooth surface.

Temperature of application:	+5 ÷ +35	°C
Humidity application:	< 85%	
Recommended thickness:	0,5 ÷ 1	mm
Recoatable after:	6	h
Tools cleaning:	with water	

Technical properties

Density:	1,75 ÷ 1,85	Kg/l
Viscosity:		
pH:	7 – 8	
Weight solids:	72%	
Theoretical yeald:	0,5	mq/Kg
Color:	White	
Gloss level:	Matt	
Pack size:	0,5 - 1 - 5 – 20	Kg

Storage



Shelf-life: not less than 2 years original tightly closed. Store away from direct sun and excessive heat.

The can should be resealed and stored tightly closed. Store it upside down after use.



Min storage temperature: +5°C

Max storage temperature: +30°C

Safety Precautions

For all information regarding product use and correct product disposal please refer to Safety Data Sheet.

Warnings

All information contained in this data sheet are based on our technical knowledge. However these indication could not have a value of guarantee for applicator considering that conditions of applying of product are out of our control. It is advisable make sure of suitability of the product making previous test.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

Company with Certified Quality System by BVQI according to UNI EN ISO 9001:2000.