




LOGGIA
industria vernici

SCHEMA TECNICA

Revisione: 22 novembre 2019



PrimaMoquette

Acrylic Matt Colorable Primer for Moquette.

General Characteristics

Composition: Primer based on special acrylic copolymers, pigments and selected fillers. Excellent coverage and yield. With a matt appearance.

use: as a colored basecoat before applying the Moquette.

Application

Preparation of the surface: before applying Primamoquette wait for 2 hours from the application of PRIMER 3D FLOOR . Proceed then as written below

Application techniques

application method: *Roller:* Dilute at max with 5% water both for the first and second coat. wait for 5-6 hours from the first and second application.



Temperature of application:	+5 ÷ +35	°C
Relative humidity of application	< 85%	
Recommended thickness:	35 ÷ 50	µm per coat
Touch dry:	0,5	h
Re-coat after:	5 ÷ 6	h
Completely cured:	24	h
Tools cleaning:	with water	

coloring

The product can be colored with the tintometric systems of the MAXXI and L'ANGELO OX line.

It is advisable to mix different batches of the same color together to avoid possible differences in tone during application.

technical properties

Density	1,3 ÷ 1,4	Kg/l
Viscosity:	8.000 ÷ 10.000	cPs
pH:	7-8	
Weight solid:	58%	
Theoretical yield	8 – 10	mq/l per coat
Color	Folder maxxi and 4OX	
Aspect	matt	
packaging	0,75 -2,5 - 4	l

Storage



The unopened product, stored intact in a dry and cool place, has a shelf life of not less than 24 months.

After use, carefully close the package and store it upside down.



Min storage temperature: +5°C

Max storage temperature: +30

safety precautions

For all information regarding product use and correct product disposal please refer to Safety Data Sheet.

Warnings: All information contained in this data sheet are based on our technical knowledge. However these indication could not have a value of guarantee for applicator considering that conditions of applying of product are out of our control. It is advisable make sure of suitability of the product making previous test.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

Company with Certified Quality System by BVQI according to UNI EN ISO 9001:2000.