

INTERMEDIAL P3D FLOOR

SCHEDA TECNICA

Revisione : 24/04/2026

Prodotto: **Intermedial P3D Floor**

Categoria: Fondi

Azienda: Loggia

General Characteristics

Water-based paint based on special acrylic copolymers, pigments, and selected fillers. Excellent coverage and yield. Matte finish.

Application

Used as a colored base on floors and tiles before applying PLASMA 3D

Preparation



Check that 4-5 hours have passed since applying PRIME P3D WALL and that the surface is perfectly clean. Apply the product as described below.



Application Methods



Roller: Dilute with up to 5% water for both the first and second coats. Wait 5-6 hours between coats.

| | | |
|-----------------------------------|----------|-------------|
| Application temperature: | +5 ÷ +35 | °C |
| Relative humidity of application: | < 85% | |
| Recommended thickness: | 35 ÷ 50 | µm per coat |
| Dust dry: | 0,5 | h |
| Repaintable after: | 5 ÷ 6 | h |
| Deep dry: | 24 | h |
| Tool cleaning: | water | |

Painting:



The product can be colored using the MAXXI line's tinting system.

It is advisable to mix different batches of the same color together to avoid possible hue differences during application.

| | | |
|--------------------|-----------------|---------------|
| Specific weight: | 1,3 ÷ 1,4 | Kg/l |
| Viscosity: | 8.000 ÷ 10.000 | cPs |
| pH: | 7-8 | |
| Solid in weight: | 58% | |
| Theoretical yield: | 8 – 10 | mq/l per coat |
| Packaging: | 0,75 - 4 | l |
| Color: | 40X Color Chart | |
| Appearance: | matt | |

Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months.

After use carefully close the package and store it upside down.



Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) –
ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

BVQI certified company for the UNI EN ISO 9001-2000 quality system.