

MAXI FOND

SCHEDA TECNICA

Revisione : 28/04/2023

Prodotto: **Maxi Fond**

Categoria: Fondi

Azienda: Loggia

General Characteristics

Idropittura murale a base di copolimeri vinilici, pigmenti e cariche selezionate ad altissima resistenza. Indicato come primer per molti decorativi

Application

Suitable as base coat for: Kymera, Domus Aurea, Domus Diamante Oro, Domus Diamante Argento, Domus Oro, Domus Argento, Domus N

Media Preparation



New surfaces: Make sure that the substrate is perfectly dry and cured - no less than 4 weeks for civil plasters and 2 weeks for premixed plasters. If necessary, level any imperfections with an appropriate exterior mortar; finally sand and clean the surfaces. Then apply a coat of FISSACRIL sealer and after 4-6 hours paint with two coats of MAXI FOND following the technical indications below.



Painted surfaces: Eliminate any traces of mold by brushing off the efflorescences after having treated them with acid. Then sanitize with a coat of MUFFACID. Remove flaky residues of old paint and, if necessary, fill and smooth imperfections with an appropriate mortar for exteriors; sand and clean surfaces. Then apply a coat of FISSACRIL sealant and after 4-6 hours with two coats of MAXI FOND as explained below.



Application Methods



Brush and Roller: Dilute 20-25% with water for both the first and second coat. Wait 5-6 hours between one application and the next.

Airless: In airless applications the dilution varies depending on the equipment and pressure used.

Warnings: Do not apply on surfaces exposed to the sun.

Application temperature:	+5 ÷ +35	°C
Relative humidity of application:	< 85%	
Recommended thickness:	50 ÷ 100	µm per coat
Dust dry:	0,5	h
Repaintable after:	5 ÷ 6	h
Deep dry:	24	h
Tool cleaning:	water	

Painting:



The product can be colored with the tintometric systems of the L'ANGELO and L'ANGELO OX lines, as well as with the universal colorants available on the market.

It is advisable to mix different manufacturing batches of the same color together to avoid possible differences in tone during application.

Specific weight:	1,60 ÷ 1,65	Kg/l
Viscosity:	25.000 ÷ 30.000	cPs
pH:	7-8	
Solid in weight:	73%	
Theoretical yield:	6 – 7	m ² /l
Packs:	2,5 - 4 - 14	l
Color:	White and cards color	
Appearance:	mat	

Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months.



After use carefully close the package and store it upside down.

Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) –
ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

BVQI certified company for the UNI EN ISO 9001-2000 quality system.