

FOND PLUS

SCHEDA TECNICA

Revisione : 21/10/2022

Prodotto: **Fond Plus** Categoria: Fondi Azienda: Loggia

General Characteristics

Primer based on quartz and special styrene-acrylic copolymers, pigments and selected fillers with very high resistance to the action of light. Made with the use of carefully selected quartz flours. Excellent coverage and resistance.

Application

Made to be used as a dyeable primer for decorations: Marmo Romano, Pelle di Luna, Hellenica, Oro prezioso, Luce di Stelle, Silver Fashion, Montenapoleone.

Preparation



New internal surfaces: Make sure that the substrate is perfectly dry and cured - not less than 4 weeks for civil plasters and 2 weeks for premixed plasters. If necessary, fill any holes or imperfections with FLYSTUK and sand; finally clean the surfaces. Then apply a coat of FISSACRIL insulation and after 4-6 hours paint with two coats of FOND PLUS following the technical instructions below.

Internal Painted Surfaces: Eliminate any traces of mold by brushing off the efflorescence after treating them with acid. Then sanitize with a coat of MUFFACID. Remove flaking residues of old paint and, if necessary, fill and smooth imperfections with FLYSTUK; sand and clean the surfaces. Then apply a coat of FISSACRIL insulation and after 4-6 hours paint with two coats of FOND PLUS following the technical instructions below.

Application Methods



Brush and Roller: Dilute 20-25% with water, if necessary apply a second coat after 5-6 hours.

Airless: In airless applications the dilution varies depending on the equipment and pressure used.

| Application temperature: | +5 ÷ +35 | °C |
|-----------------------------------|----------|-------------|
| Relative humidity of application: | < 85% | |
| Recommended thickness: | 50 ÷ 100 | µm per coat |
| Dust dry: | 0,5 | h |
| Repaintable after: | 5 ÷ 6 | h |
| Deep dry: | 24 | h |
| Tool cleaning: | water | |

Painting:



The product can be colored with the tinting systems of the L'ANGELO and L'ANGELO OX lines, as well as with the universal dyes available on the market.

It is advisable to mix different manufacturing batches of the same color with each other to avoid possible differences in shades during application

| Specific weight: | 1,65 ÷ 1,72 | Kg/I |
|-----------------------------|-----------------------------|---------------|
| Viscosity: | 25.000 ÷ 30.000 | cPs |
| pH: | 7-8 | |
| Solid in weight: | 73% | |
| Theoretical yield: | 8 -10 | mq/l per coat |
| Recommended coats of paint: | Bianco e Colori di Cartella | |
| Color: | Mat | |
| Appearance: | 0,750- 4 | |

Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months.

After use carefully close the package and store it upside down.

Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

<u>Warnings</u>

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

Loggia Industria Vernici S.r.I. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

BVQI certified company for the UNI EN ISO 9001-2000 quality system.