

RISANARE LAVABILE

SCHEDA TECNICA

Revisione : 07/09/2023

Prodotto: **Risanare Lavabile**
Categoria: Idropitture per Interni
Azienda: Loggia

General Characteristics

Breathable water-based paint based on acrylic emulsions and with specific anti-mould agents with a great action on reducing the process of regrowth of efflorescence. It has a high whiteness and hiding power and excellent resistance to washing. Good applicability. Suitable in environments where food is produced, processed and distributed. RISANARE LAVABILE complies with the UNI 11021:2002 standard "Paints and varnishes. Products and systems for painting environments with the presence of food (test report n.018/2016 issued by TERMOTECH ECO srl). to guarantee the compliance of the surfaces according to the HACCP protocol to prevent possible food contamination

Application

Suitable for painting all internal wall surfaces, in humid environments where mold formation is easy. Applicable on plasters based on hydraulic binders, gypsum or plasterboard, and conglomerates of various absorbent natures, both new and old, provided they do not crumble.

Surface Preparation



New internal surfaces: Make sure that the surface is perfectly dry and seasoned - no less than 4 weeks for civil plasters and 2 weeks for premixed plasters. If necessary fill any holes or imperfections with FLYSTUK and sand; finally clean the surfaces. Then apply a coat of FISSACRIL sealer and after 4-6 hours paint with two coats of RISANARE LAVABILE following the technical indications below.



Internal Painted Surfaces: Eliminate any traces of mold by brushing off the efflorescences after having treated them with acid. Then sanitize with a coat of MUFFACID. Remove flaky residues of old paint and, if necessary, fill and smooth imperfections with FLYSTUK; sand and clean surfaces. Then apply a coat of FISSACRIL sealer and after 4-6 hours paint with two coats of RISANARE LAVABILE following the technical indications below.



Application Methods



Brush: Dilute 30-35% with water for both the first and second coat. Wait 5-6 hours between one application and the next.



Roller: Dilute 20-25% with water for both the first and second coat. Wait 5-6 hours between one application and the next.



Airless: In airless applications the dilution varies depending on the equipment and pressure used.

Application temperature:	+5 ÷ +35	°C
Relative humidity of application:	< 85%	
Recommended thickness:	35 ÷ 50	µm per coat
Dust dry:	0,5	h
Repaintable after:	5 ÷ 6	h
Deep dry:	24	h
Tool cleaning:	water	

Painting:



The product can be colored with universal dyes available on the market.

It is advisable to mix different manufacturing batches of the same color together to avoid possible differences in tone during application.

Specific weight:	1,60 ÷ 1,65	Kg/l
Viscosity:	15.000 ÷ 20.000	cPs
pH:	7 – 8	
Solid in weight:	68%	
Theoretical yield:	9 – 11	m ² /l
Washability	>10000	brush strokes
Color:	white	
Appearance:	mat	
Packing:	4 – 14	l

Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months.



After use carefully close the package and store it upside down.

Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) –
ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

BVQI certified company for the UNI EN ISO 9001-2000 quality system.