

RISANARE ACRIL

SCHEDA TECNICA

Revisione : 28/02/2025

Prodotto: **Risanare Acril**
Categoria: Linea Risanare
Azienda: Loggia

General Characteristics

Super-washable water-based paint based on acrylic emulsions, with the addition of specific anti-mold agents, which strongly reduce the regrowth process of efflorescence. It has a high whiteness, high covering power and excellent resistance to washing. Good applicability. Suitable for environments where food is produced, processed and distributed.

RISANARE ACRIL complies with the UNI 11021:2002 "Paints and varnishes" standard. Products and systems for painting environments with the presence of food (Test report n.018/2016 released by TERMOTECH ECO srl), to guarantee the conformity of surfaces according to the HACCP protocol to prevent possible food contamination.

Application

Suitable for painting all internal wall surfaces, in humid environments where mold formation is easy. Applicable on plasters based on hydraulic binders, gypsum or plasterboard, and absorbent conglomerates of various kinds, both new and old, as long as they are not chalky. The presence of additives with a broad spectrum of action protects the walls from the formation of mold (compliant with the UNI EN 15457 standard - resistance to the formation of fungi)

Media Preparation



New Internal Surfaces: Make sure the surface is perfectly dry and cured - no less than 4 weeks for civil plasters and 2 weeks for plasters premixed. If necessary, fill any holes or imperfections with FLYSTUK e sand; finally clean the surfaces. Then apply a coat of RISANARE FIX insulation FIX and after 4-6 hours paint with two coats of RISANARE ACRIL following the instructions technical indications given below.



Painted Internal Surfaces: Eliminate any traces of mold with RISANARE CID. Then sanitize with a coat of RIARE STOP. Remove flaking residues of old ones paints and, if necessary, fill and smooth the imperfections with FLYSTUK; sand and clean surfaces. Then apply a coat of RISANARE FIX L insulation and after 4-6 hours paint with two coats of RISANARE ACRIL following the technical instructions below reported.

Application Methods



Brush: Dilute 30-35% with water for both the first and second coat.

Wait 5-6 hours between one application and the next.

Roller: Dilute 20-25% with water for both the first and second coat. Wait

5-6 hours between one application and the next.

Airless: In airless applications the dilution varies depending on the equipment and of the pressure used

Application temperature:	+5 ÷ +35	°C
Relative humidity of application:	< 85%	
Recommended thickness:	35 ÷ 50	µm per coat
Dust dry:	0,5	h
Repaintable after:	6 ÷ 8	h
Deep dry:	24	h
Tool cleaning:	water	

Painting:



Testo da inserire

Specific weight:	1,40 ÷ 1,60	Kg/l
Viscosity:	10.000 ÷ 15.000	cPs
CLASSIFICATION ACCORDING TO EN 13300 Resistance to wet brushing ISO 11998	Classe 1 < 5 micron 200 cicli	
Brilliance (Gloss) ISO 2813	Opaco < 10 (geometria 85°)	
CLASSIFICATION ACCORDING TO UNI 10795 Covering power (Ywhite/Yblack) UNI 11271	Classe 2 98 < c< 99,5	
pH:	7-8	
Solid in weight:	55%	
Theoretical yield:	9-11	mq/l
Color:	white	
Appearance:	mat	
Packs:	4 – 14	

Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months.



After use carefully close the package and store it upside down.

Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

Specifications items

Washable, sanitizing and sanitizing acrylic. Preparation of the support with a coat of RISANARE FIX insulation. Application of two coats of RISANARE ACRIL in the quantity determined by the absorption of the support until a suitable dry film thickness is obtained. Everything must be carried out in compliance with the application regulations, with a cost of €..... per square meter including material and installation

Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

BVQI certified company for the UNI EN ISO 9001-2000 quality system.