

# UNA MANO UNICA

## SCHEDA TECNICA

Revisione : 03/09/2025

Prodotto: **UNA Mano Unica**

Categoria: Idropitture per Interni

Azienda: Loggia

**Universal one-coat paint for walls and plasterboard, ready to use.**

### General Characteristics

Its formulation based on acrylic-vinyl resins in aqueous dispersion, pigments and covering fillers, makes the product particularly suitable for plasterboard, both new and old, civil plasters, gypsum plasters, walls already painted even with strong colors. It suffices one coat to grant high coverage and excellent whiteness.

### Use

Universal water-based paint for internal use; it does not require a primer and guarantees perfect adhesion on walls and plasterboard, ready for use. Thanks to its high covering power, it allows you to obtain excellent coverage with one hand.

### Preparation



**New Internal Surfaces:** Make sure that the substrate is perfectly dry and cured - not less than 4 weeks for civil plasters and 2 weeks for premixed plasters. If necessary, fill any holes or imperfections with FLYSTUK and sand; finally clean. On particularly absorbent substrates, apply a coat of UNA PIGMENTED fixative.



**Internal Painted Surfaces:** Eliminate any traces of mold by brushing off the efflorescence. Then sanitize with a coat of MUFFACID. Remove flaking residues of old paint and, if necessary, fill and smooth imperfections with FLYSTUK; sand and clean the surfaces. If the substrate is crumbly, apply a coat of UNA PIGMENTED insulation.



### Application Methods



Brush: Dilute 25-30% with water for both the first and second coat. Wait 5-6 hours between one application and the next.



Roller: Dilute 20% with water for both the first and second coat. Wait 5-6 hours between one application and the next.



Airless: In airless applications the dilution varies depending on the equipment and pressure used

Application temperature:	+5-+35	°C
Relative humidity of application:	<85	
Recommended thickness:	30-50	µm per coat
Dust dry:	0,5	h
Repaintable after:	5-6	h
Deep dry:	24	h
Tool cleaning:	water	

### **Technical features**

Specific weight:	1.62	Kg/l
Viscosity:	12000-15000	cPs
pH:	7-8	
Solid in weight:	68	%
Theoretical yield:	14-15	mq/l
Color:	white	
Appearance:	Silky satin	
Packaging:	4-14	l

### **CLASSIFICATION ACCORDING TO EN 13300**

Measure	Standard	Classification	Result
Resistance to wet brushing ISO 11998		CLASS 3	[> 20 µm e < 70 µm 200 cycles]
GLOSS ISO 2813		MATT	< 10 (geometry 85°)
Maximum particle size ISO 1524		THIN	<100

### **CLASSIFICAZIONE SECONDO UNI 10795**

Measure	Standard	Classification	Result
covering power (Ywhite/Yblack)	UNI 11271	good	96 < C < 98
Diffusion of water vapor (breathability)	WDD ISO 7783-2	high	>150 g/m2 in 24 h

**Storage:** \_\_\_\_\_



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months.



After use carefully close the package and store it upside down.

Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

## **Safety Precautions:**

---

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

## **Warnings**

---

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

**Loggia Industria Vernici S.r.l.** Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. [www.loggia.it](http://www.loggia.it), E-mail [commerciale@loggia.it](mailto:commerciale@loggia.it).

**BVQI certified company for the UNI EN ISO 9001-2000 quality system.**