



LOGGIA
industria vernici

TECHNICAL DATA SHEET

Issue Date: January 14



Aria soft

Vinyl Interior Emulsion.

General Characteristics

Composition: ARIA SOFT is a vinyl water-based interior wall paint, formulated with high resistance fillers. Due to its water vapour permeability it is a moisture resistant product. It provides both the professional and the private with a good hiding, not yellowing and easy to apply product.

Recommended Usage: It is recommended for interior application on walls and ceilings of primed plaster, suitably prepared wallboard and masonry etc.

Preparation

Surface Preparation:



Interior new surfaces: All surfaces must be dry and cured according to the supplier's recommendations – usually about 30 days. Rough surfaces can be filled with putty FLYSTUK to provide a smooth surface; Ensure the support to be coated is clean with dust and dirt removed. One coat of primer FISSAMUR should be applied followed by two coats of ARIA SOFT. For the application please refer to the technical methods given below.



Interior coated surfaces: Any mildew should be removed before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the surface to dry before applying a coat of fungicide MUFFACID. It requires the use of proper protective equipment. Existing peeled paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull. Coatings in a poor condition should be removed completely. Fill cracks and holes with putty FLYSTUK; then sand smooth. Remove all sanding dust. One coat of primer FISSAMUR should be applied followed by two coats of ARIA SOFT. For the application please refer to the technical methods given below.

Product Application

Methods:



Brush: Use a nylon/polyester or a natural bristle brush. Thin by up to 20-30% by volume with water both the first and the second coat.

Roller: Use a 3/8" - 3/4" nap synthetic or lamb's wool roller cover. Thin by up to 20% by volume with water both the first and the second coat.



Airless: Pressure: 140 – 160 bar (2000 – 2350 psi). Tip: 0.017” – 0.021”. Dilution depends on the airless system in use. A trial application is strongly recommended prior to the commencement of work.

Temperature of application:	+5 ÷ +35 °C	41 ÷ 95 °F
Relative humidity of application:	< 85%	
Dry film thickness:	35 ÷ 40 µm per coat	1.4 ÷ 1.6 mils per coat
Touch dry:	30 minutes	
Recoat after:	4 ÷ 5 hours	
Completely Cured:	21 days	
Cleaning tools:	by water	

Colouring



White can be tinted with Universal Stainers to obtain customized shades. The colouring of the product is recommended only in order to realize either off white or pastel colours.

Care should be taken when one uses different batches of the same colour. Mix them together to ensure colour uniformity during application.

Technical Properties


Density:	1.68 ÷ 1.71 Kg/L	
Viscosity:	20000 ÷ 25000 cPs	
pH:	7-8	
Weight Solids:	68%	
Coverage:	7 – 8 m ² /L	286 – 330 sq ft/gal
Colour:	White	
Gloss Levels:	Matt	
Pack Size:	2.5 - 4 – 14 L	

Storage



Shelf-life: 2 years in original tightly closed containers away from direct sunlight and excessive heat.

The can should be resealed and stored tightly closed to prevent evaporation of the product and entry of air. Store it upside down after use.



Min storage temperature: +5°C (41°F)

Max storage temperature: +30°C (86°F)

Safety Precautions

Refer to the Material Safety Data Sheet before use.

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects. For more information about how to remove old lead paint safety contact your local health authority.

General Information

Every care is taken to ensure that the information provided in this technical data sheet is accurate. **Loggia Industria Vernici S.r.l.** takes no responsibility for the results obtained through the use of this product in as much as it is not possible for **Loggia Industria Vernici S.r.l.** to check or control the application method used. For this reason, we recommend that you check carefully that each product chosen, is suitable for each individual use to which it is put.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

Company with Certified Quality System by BVQI according to UNI EN ISO 9001:2000.