

INTONACHINO ACRILICO

SCHEDA TECNICA

Revisione : 28/08/2023

Prodotto: **Intonachino acrilico**
Categoria: Rivestimenti a Spessore
Azienda: Loggia

General Characteristics

Plastic coating for external surfaces based on acrylic resins in emulsion, silica fillers of various granulometry and inorganic pigments with high resistance to light. Excellent resistance to atmospheric agents and alkalis, good applicability and elasticity, it adheres perfectly to the treated surface giving high water repellency and protection over time.

Application

Suitable for the protection of external masonry surfaces to give them a rustic effect. Applicable on plasters based on hydraulic binders, concrete and absorbent conglomerates of various kinds, both new and old, provided they are not chalky.

Preparation



New External Surfaces: Make sure the surface is perfectly dry and cured – no less than 4 weeks for civil plasters and 2 weeks for premixed plasters. If necessary, level any imperfections with an appropriate exterior mortar, sand and clean the surfaces, then apply a coat of FISSACRIL sealer and after 4-6 hours spread a layer of acrylic Intonachino following the technical indications below.



Painted External Surfaces: Eliminate any trace of mold by brushing away the efflorescences after having treated them with acid. Then sanitize with a coat of MUFFACID. Remove flaky residues of old paint and, if necessary, fill and smooth imperfections with an appropriate mortar for exteriors; sand and clean surfaces, then apply a coat of FISSACRIL sealer and after 4-6 hours spread a layer of acrylic Intonachino following the technical indications below.



In case of very crumbling surfaces it is advisable to replace FISSACRIL with ISOL 45 solvent-based sealer.

Application Methods



American trowel: Spread the product as it is with a smooth spreader, being guided by the thickness of the grain, distributing it evenly.

Sponge pad: During the drying phase, refine the surface with a plastic float or sponge pad (the latter compacts the product more closing the spaces between the grains left by the trowel action).

Warnings: Do not apply on surfaces exposed to the sun

Application temperature:	+5 ÷ +35	°C
Relative humidity of application:	< 85%	
Recommended thickness:	2 ÷ 4	µm per coat
Dust dry:	1	h
Repaintable after:		h
Deep dry:	48	h
Tool cleaning:	water	

Painting:



The product can be colored with the tinting systems of the MAXXI and L'ANGELO OX ranges.

It is advisable to mix different manufacturing batches of the same color together to avoid possible differences in tone during application.

Specific weight:	1,85 ÷ 2	Kg/l
Viscosity:	30.000 ÷ 40.000	cPs
pH:	7-8	
Solid in weight:	81%	
Theoretical yield:	1,5 – 3	m ² /l
Granulometry:	1,0 ÷ 1,4	mm
Color:	white and card colors	
Appearance:	Opaco	
Packing	5 - 23	kg

Storage:



The unopened product, stored intact in a dry and cool place, has a storage life of not less than 24 months.



After use carefully close the package and store it upside down.

Minimum storage temperature: + 5 ° C

Maximum storage temperature: + 30 ° C

Safety Precautions:

For all information relating to the handling of the product as well as its correct disposal, please refer to the Safety Data Sheet.

Warnings

The information contained in this sheet is provided to the best of our technical knowledge. However, these indications and suggestions cannot have the value of a guarantee for the applicator, since the conditions of use of the product are beyond our direct control. It is therefore advisable to ascertain the suitability of the product for the specific case with preliminary tests.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) –
ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

BVQI certified company for the UNI EN ISO 9001-2000 quality system.