




LOGGIA
industria vernici

TECHNICAL DATA SHEET

Issue Date: January 14



Intonachino ai Silossani

High Build Decorative Coating based on modified Silicon Resins.

General Characteristics

Composition:

INTONACHINO AI SILOSSANI is a decorative coating, formulated with different size aggregates used to produce a high build finish. It incorporates the latest state-of-the-art technology to provide a masonry coating with excellent vapour permeability, together with a high level of water repellence and excellent weather and chemical resistance. It represents an innovative alternative solution to mineral products, e.g. limewashes or silicate paints. INTONACHINO AI SILOSSANI creates a porous coating that adheres perfectly to both mineral surfaces and old synthetic paints.

Recommended Usage:

It is recommended for exterior masonry walls, new or old plasters based on hydraulic binders and concrete. Due to its high water repellence INTONACHINO AI SILOSSANI is heartily recommended for all those buildings staying near seaside.

Preparation

Surface Preparation:




Exterior new surfaces: All surfaces must be dry and cured according to the supplier's recommendations – usually about 30 days. Rough surfaces can be filled with external putty or a mixture of white cement and fine sand (in the ratio of 1:3) to provide a smooth surface; Ensure the support to be coated is clean with dust and dirt removed. One coat of primer ISOLANTE SILOSSANICO should be applied followed by one coat of INTONACHINO AI SILOSSANI. For the application please refer to the technical methods given below.



Exterior coated surfaces: Any mildew should be removed before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the surface to dry before applying a coat of fungicide MUFFACID. That requires the use of proper protective equipment. Any synthetic coating must be removed completely. In fact it would prevent any chemical reaction from happening. Fill cracks and holes with external putty or a mixture of white cement and fine sand (in the ratio of 1:3); then sand smooth. Remove all sanding dust. One coat of primer ISOLANTE SILOSSANICO should be applied followed by one coat of INTONACHINO AI SILOSSANI. For the application please refer to the technical methods given below.

Product Application

Methods:



Putty knife or steel trowel: Apply the product as such by a smooth putty knife or steel trowel. During withering scrub the surface with plastic or spongy trowel (the latter makes the surface more compact).



In order to better protect INTONACHINO AI SILOSSANI from bad weather conditions and to increase its beauty you can apply on it a coat of decorative coating EFFETTO TAMPONATO SILOSSANICO. Please refer to technical data sheet for methods and application.

Warning: Do not paint in direct sun or on a hot surface. Do not apply to wet surfaces.

Temperature of application:	+5 ÷ +35 °C	41 ÷ 95 °F
Relative humidity of application:	< 85%	
Dry film thickness:	2 ÷ 4 mm	
Touch dry:	1 hour	
Completely Cured:	21 days	
Cleaning tools:	by water	

Colouring



This product can be coloured with Tinting Systems L'ANGELO and L'ANGELO OX. In addition it can be tinted with Universal Stainers to obtain customized shades.

Care should be taken when one uses different batches of the same colour. Mix them together to ensure colour uniformity during application.

Technical Properties

Density:	1.35 ÷ 1.5	Kg/L	
Viscosity:	30000 ÷ 40000	cPs	
pH:	7 - 8		
Weight Solids:	84%		
Coverage:	0.35 – 0.7	m ² /Kg	
Colour:	Many Colours		
Gloss Levels:	Matt		
Pack Size:	5 - 25	Kg	
Texture Grade	0.6 ÷ 0.8 / 1 ÷ 1.4	mm	
Vapour Permeability	Sd=0,5	[< 2]	m (DIN 52615)
Capillary Absorption	W ₂₄ =0,32	[< 0,5]	Kg /m ² /h ^{0,5} (DIN 52617)
Künzel's Diagram	Sd x W ₂₄ =0,16	[<0,2]	Kg /m /h ^{0,5} (DIN 18550)

Storage



Shelf-life: 2 years in original tightly closed containers away from direct sunlight and excessive heat.

The can should be resealed and stored tightly closed to prevent evaporation of the product and entry of air. Store it upside down after use.



Min storage temperature: +5°C (41°F)

Max storage temperature: +30°C (86°F)

Safety Precautions

Refer to the Material Safety Data Sheet before use.

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects. For more information about how to remove old lead paint safety contact your local health authority.

General Information

Every care is taken to ensure that the information provided in this technical data sheet is accurate. **Loggia Industria Vernici S.r.l.** takes no responsibility for the results obtained through the use of this product in as much as it is not possible for **Loggia Industria Vernici S.r.l.** to check or control the application method used. For this reason, we recommend that you check carefully that each product chosen, is suitable for each individual use to which it is put.

Loggia Industria Vernici S.r.l. Via Colle d'Alba di Levante – 04016 B.go S. Donato - Sabaudia (LT) – ITALY

Tel. (+39) 0773 562212, Fax (+39) 0773 562034. www.loggia.it, E-mail commerciale@loggia.it.

Company with Certified Quality System by BVQI according to UNI EN ISO 9001:2000.